

Product Bulletin

CASS POLYMERS

ADTECH
Plastic Systems
SC-9001 Registered



Phone: 800 344 7776
Fax: 248 588 5909
815 West Shepherd Street
Charlotte, MI 48813-0523
plastic@casspolymers.com
www.casspolymers.com

EA-616
EPOXY WELD ADHESIVE

0302

DESCRIPTION

EA-616 EPOXY WELD ADHESIVE is a two component adhesive system developed for bonding similar and dis-similar substrates at room temperature. EA-616 is a convenient 1 to 1 mix ratio with color change to indicated positive mix. The black resin and white hardener when properly mixed is a uniform dark gray. EA-616 has a relatively fast set (8-13 minutes @ 77°F) and reaches handling strength within 1½ to 3 hours. EA-616 exhibits excellent bond strength to such unusual bonds as fiberglass, graphite epoxy, rubber, thermo plastics, stainless steel, aluminum, oily metal and other difficult bonds.

HANDLING CHARACTERISTICS @ 25°C/77°F

Mix Ratio (by weight or volume)	100R/100H
Density.....	9.4 lb/gal
Specific Gravity	1.13 gms/cc
Work Life - 4 oz	8-13 minutes
Handling Strength	1½-3 hours
Cure (complete)	16-24 hours

PHYSICAL PROPERTIES

Ultimate Tensile Strength (ASTM D-638)	3,563 psi
Tensile Elongation (ASTM D-638)	1.14%
Tensile Modulus (ASTM D-638).....	622,400 psi
Impact Strength (ASTM D-256.93a)	5.7 in-lbf/in
Heat Defection Temperature (@ 66 psi) (ASTM D-648.88)	115.1°F
@ 264 psi (ASTM D-648.88)	108.0°F
Compressive Strength (ASTM D-695.91)	8,104 psi
Compressive Modulus (ASTM D-695.91)	223,300 psi
Coefficient of Thermal Expansion (ASTM D-696.91)	29.7 x 10 ⁻⁶ in/in°F
Flexural Strength (ASTM D-790).....	5,953 psi
Flexural Modulus (ASTM D-790).....	305,500 psi
Lap Shear Strength (ASTM D-1002).....	1,596 psi
(Metal to Metal)	
Peel Resistance (ASTM D-1876)	6.474 lbs/in

SELLER CANNOT ANTICIPATE ALL CONDITIONS UNDER WHICH SELLER'S PRODUCTS, OR THE PRODUCTS OF OTHER MANUFACTURERS IN COMBINATION WITH SELLER'S PRODUCTS, MAY BE USED. SELLER ACCEPTS NO RESPONSIBILITY FOR RESULTS OBTAINED BY THE APPLICATIONS OF SELLER'S PRODUCTS OR THE SAFETY AND SUITABILITY OF SELLER'S PRODUCTS, EITHER ALONE OR IN COMBINATION WITH OTHER PRODUCTS. USERS ARE ADVISED TO MAKE THEIR OWN TEST TO DETERMINE THE SAFETY AND SUITABILITY OF EACH SUCH PRODUCT OR PRODUCT COMBINATION FOR THEIR OWN PURPOSES. UNLESS OTHERWISE AGREED IN WRITING, SELLER DELIVERS THE PRODUCTS WITHOUT WARRANTY OF ANY NATURE, STATED OR IMPLIED, AND BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR LOSS OR DAMAGE ARISING FROM THE HANDLING AND USE OF SAID PRODUCTS, WHETHER USED ALONE OR IN COMBINATION WITH OTHER PRODUCTS. PURCHASER WAIVES ANY CLAIM AGAINST SELLER FOR DIRECT, INDIRECT, CONSEQUENTIAL OR EXEMPLARY DAMAGES AGAINST SELLER, INCLUDING WITHOUT LIMITATION, DAMAGE WHICH MAY OCCUR AS A RESULT OF PURCHASER'S USE OR MISUSE OF THE PRODUCT OR THE PRODUCT'S FAILURE TO CONFORM TO ANY PARTICULAR SPECIFICATIONS.