



# EP-300

## HIGH TEMPERATURE EPOXY PLANK®

### PRODUCT BULLETIN



www.CASSpolymers.com  
31200 Stephenson Hwy

800.344.7776  
Madison Heights MI 48071

TCC@CASSpolymers.com  
Ph 248.588.2270 Fax 248.588.5909

#### DESCRIPTION:

**Epoxy Plank EP-300** is a light blue high temperature epoxy tooling plank designed for building aerospace master models, lay-up tools for medium and high temperature prepregs, vacuum-form tooling and other high temperature tooling. This high temperature tooling plank has an excellent surface finish, good edge definition, and is easy to CNC machine. **EP-300** Epoxy Plank is recommended for tooling up to 300°F.

#### TYPICAL PROPERTIES:

Color.....	Light Blue
Hardness @ 75°F.....	78 Shore D
Density .....	49.6 lbs/cu ft
Flexural Strength.....	8,169 psi
Flexural Modulus.....	392,700 psi
Tensile Strength .....	6,167 psi
Elongation .....	1.6%
Compressive Strength.....	12,590 psi
Compressive Modulus.....	438,100 psi
Heat Deflection Temperature @ 66 psi.....	320°F/160°C
Tg by TMA.....	325°F/163°C
Coefficient of Linear Thermal Expansion (from 30°C to 100°C) .....	44.1 x 10 <sup>-6</sup> in/in/°C
Coefficient of Linear Thermal Expansion (from -30°C to 30°C).....	29 x 10 <sup>-6</sup> in/in/°C

High Temperature Adhesive System ..... EL-336 R/H

Standard Size Available: 2", 3", 4"T x 24"W x 60"L

STORAGE: Store all Tooling Planks on a flat surface at 60°F-100°F.

**RECOMMENDED CNC MACHINING INFORMATION**

(Carbide Cutters are highly recommended)

	<b>Inches per minute (Feed IPM)</b>	<b>Plunge (mm)</b>	<b>Spindle Speed (rpm)</b>
2" E-Mill for Roughing	100	25	6000
3/4" Ball	75	20	3000+
1/2" Ball	60-75	10-20	3000+
1/2" x 1/32" R	40	20	4000
1/4" Ball	60	10-20	5000

These are possible recommendations. There may be some variance depending on cutters and CNC mill capabilities.

**CUTTING SUGGESTIONS FOR TOOLING PLANKS**

**CUTTING HORIZONTALLY ON A PLANNER MILL:** Head is a 10 insert, 8" in diameter. For best results use 5 inserts. Inserts are SFE-42E-10J-C5. We have found a C2 Carbide insert does not chip as easily. RPM 2200-2400 – table feed 50-55 inches per minute. Some modifications may be needed.

**SAW BLADES:** A carbide-tipped, positive rake saw blade with air slots should be used, if possible. We suggest alternate top bevel ATB or triple chip grind TCG rpm, depending on the saw. We suggest 3,500 max rpm. Check with manufacturer on saw and blade size.

- 12" blade, 48 teeth
- 16" blade, 48 teeth
- 18" blade, 60 teeth

When sawing, you may need to back part away from blade to relieve heat and binding, then proceed with cut. It may be necessary to take more than one cut to achieve best finish.

EP-300 Tech/Revised 3/30/07  
Supersedes 3/6/07



Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. Seller accepts no responsibility for results obtained by the application of seller's products or the safety and suitability of seller's products, either alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, seller delivers the products without warranty of any nature, stated or implied, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of said products, whether used alone or in combination with other products. Purchaser waives any claim against seller for direct, indirect, consequential or exemplary damages against seller, including without limitation, damage which may incur as a result of purchaser's use or misuse of the product or the products failure to conform to any particular specifications.